

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A01N 43/80, C08K 5/47, C07D 275/04	A1	(11) International Publication Number: WO 96/22023 (43) International Publication Date: 25 July 1996 (25.07.96)
(21) International Application Number: PCT/GB95/02951 (22) International Filing Date: 18 December 1995 (18.12.95) (30) Priority Data: 9500856.1 17 January 1995 (17.01.95) GB (71) Applicant (for all designated States except US): ZENECA LIMITED [GB/GB]; 15 Stanhope Gate, London W1Y 6LN (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): AUSTIN, Peter, William [GB/GB]; 45 Randale Drive, Bury, Lancashire BL9 8NF (GB). (74) Agents: FAWKES, David, Melville; Intellectual Property Group, Zeneca Specialties, P.O. Box 42, Hexagon House, Blackley, Manchester M9 8ZS (GB) et al.		(81) Designated States: AL, AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: COMPOSITION AND USE (57) Abstract The use of a 2-(C ₃₋₅ -alkyl)-BIT or 2-aralkyl-BIT such as 2-phenylethyl-BIT as a fungicide for plastics materials. 2-n-butyl-BIT is preferred.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

COMPOSITION AND USE

The present invention relates to the use of 2-alkyl- and 2-aralkyl-1,2-benzisothiazolin-3-ones as biocides for the protection of plastics materials and especially their use as fungicides, including compositions thereof. 1,2-benzisothiazolin-3-ones (hereinafter "BIT") and their use as biocides are well known to the art.

5 GB 848,130 discloses BIT's containing inter alia a 2-alkyl substituent containing at least 4 carbon atoms or a 2-benzyl group substituted by halogen. These compounds are said to possess useful anti-bacterial and antifungal activity and are of use as pharmaceutical, veterinary and agricultural biocides.

10 US 3,517,022 discloses BIT's containing inter alia a 2-alkyl substituent having from 4 to 24 carbon atoms and where the phenyl ring of the BIT is substituted by halogen, C₁₋₄-alkyl or C₁₋₄-alkoxy. Such compounds are said to be useful industrial biocides, especially agricultural fungicides and also pesticides.

GB 1,531,431 discloses 2-(C₁₋₃-alkyl)-BIT's and their use as industrial biocides, including fungicides, in aqueous systems and paint films.

15 More recently, EP 475,123 has proposed the use of 2-(n-C₆₋₈-alkyl)-BIT's as industrial biocides and especially fungicides for paint and plastics materials. These compounds are said to be particularly effective against *Scopulariopsis brevicaulis*. Furthermore, the 2-(n-C₆₋₈-alkyl)-BIT's are stated to have much higher activity against mould fungi than the 2-(C₁₋₃-alkyl)-BIT's of GB 1,531,431. Indeed, data is presented
20 which shows that the 2-n-octyl-BIT is more active than 2-n-hexyl-BIT and both are significantly more active than 2-methyl-BIT against fungi and yeast.

It has now been found that some 2-alkyl-BIT derivatives are very active against fungal deteriogens for plastics materials and contrary to the recent teachings of EP 475,123 the activity of these compounds against the important fungi in plastics
25 materials actually decreases with increasing number of carbon atoms in the 2-alkyl chain. It has also been found that some 2-aralkyl-BIT derivatives are also very active against these particular fungi in plastics materials.


A further important property which is required by a fungicide for plastics materials is the ability to withstand the processing conditions to which the material is
30 subjected during fabrication processes such as extrusion. This generally involves heating the plastics materials at temperatures in excess of 140°C. It is therefore important that the fungicide exhibits high temperature stability and low volatility under such conditions.

It has now been found that the more active BIT-derivatives exhibit too high a volatility to make them suitable as fungicides for plastics materials and that the 2-alkyl group must contain not less than 3 carbon atoms. The 2-aralkyl-BIT derivatives exhibit acceptable and very advantageous low volatility.

5 A still further important requirement for a fungicide for plastics materials is that it must be capable of formulation with plasticisers and stabilisers which are commonly used in the plastics materials fabrication industry and that the fungicide exhibits high resistance to discoloration in use and longevity of effect under various conditions to which the treated plastics materials are exposed in use.

10 It has been found that certain 2-alkyl and 2-aralkyl BIT derivatives (hereinafter "ABIT") meet the aforementioned requirements especially in respect of volatility and activity against fungal deteriorogens for plastics materials.

According to the invention there is provided the use of 2-alkyl- and 2-aralkyl-BIT derivatives of Formula 1 as fungicides for plastics materials



20 wherein

R¹ is hydroxy, halogen, C₁₋₄-alkyl or C₁₋₄-alkoxy;

R is C₃₋₅-alkyl, cycloalkyl or aralkyl which contains at least 2 carbon atoms linking the aryl group to the nitrogen atom and where the alkyl or aryl group may be optionally substituted; and

25 n is from 0 to 4.

Preferably, halogen is bromine and especially chlorine.

The substituent R¹ is preferably located in the 5- and/or 6- position of the BIT molecule and is especially located in the 6- position.

An especially preferred embodiment is where n is zero.

30 When R is alkyl it may be linear or branched but is preferably linear. Examples of such alkyl groups are n-propyl, iso-propyl, n-butyl, iso-butyl, tert-butyl, n-amyl, iso-amyl and 2-methylbutyl.

When R is cycloalkyl it is preferably cyclopentyl.

35 When R is alkyl, it preferably contains 4 carbon atoms and is especially n-butyl.

When R is aralkyl, it is preferably 2-arylethyl and especially 2-phenylethyl.

When the alkyl group or the aryl moiety of the aralkyl group represented by R is substituted, the substituent is preferably hydroxy, halogen or nitrile. It is preferred, however, that the alkyl group and the aryl moiety are unsubstituted.

5 Particularly useful effects have been obtained when R is n-butyl and especially 2-phenylethyl.

The ABIT is incorporated in the plastics materials to be protected at a concentration from that at which the ABIT exhibits some control of fungal growth up to much higher concentrations. Preferably, the amount of ABIT is less than 1.5%, more
10 preferably less than 1.0%, particularly less than 0.7% and especially less than 0.5% by weight based on the weight of plastics material. Useful effects have been obtained when the amount of ABIT is less than 0.25% and even less than 0.1% by weight of the plastics materials.

The ABIT must be stable to the temperature conditions at which the
15 plastics material is fabricated. Preferably, it is stable above 180°C, more preferably above 200°C and especially above 250°C. It is preferred that the weight loss on heating from 25 to 160°C at a heating rate of 10°C/minute is less than 10%, more preferably less than 6% and especially less than 2%.

As noted hereinbefore the ABIT is commonly formulated with a plasticiser
20 or stabiliser which is suitable for use with the plastics material to be protected. Thus, according to a further aspect of the invention there is provided a composition comprising a plasticiser or stabiliser and an ABIT.

The plasticiser or stabiliser is any of those commonly used in the plastics
25 fabrication industry. It is preferably a liquid and is especially an ester derived from mono- and di-carboxylic acids and linear or branched alcohols, epoxidised fatty acid ester and epoxidised vegetable oils. Examples of these plasticisers and stabilisers are phthalates, particularly dialkyl phthalates, such as dioctyl phthalate, di-(2-ethylhexyl) phthalate, dinonylphthalate and di-isodecylphthalate, epoxidised octyl stearate and epoxidised soya bean oil; and the phosphate esters of general formula $O=P(OR^2)_3$
30 wherein R^2 is hydrocarbyl, especially aryl such as phenyl and more especially C_{1-4} -alkyl which may be linear or branched. Examples of such alkyl groups are methyl, ethyl, isopropyl, butyl and tert-butyl. Examples of other esters are adipates, sebacates and trimellitates of linear or branched alcohols, especially those alcohols containing from 8 to 10 carbon atoms and low molecular weight oligo- and poly-esters such as those
35 obtainable by reacting 1,3-butanediol with adipic acid.

The composition may contain more than one ABIT. It may also contain other fungicides and/or algicides in order to broaden the spectrum of activity of the composition. Examples of other fungicides and algicides include 2-alkyl-BIT's such as 2-(n-hexyl)-BIT, 2-(2-ethylbutyl)-BIT, 2-(2-ethylhexyl)-BIT, 2-octylisothiazolin-3-one, oxy-
 5 bis-10,10-phenoxarsine, trichloromethylmercaptophthalimide; ureas such as 2-(3,4-dichlorophenyl)-1,1-dimethylurea and 2-(4-isopropylphenyl)-1,1-dimethylurea; 4-alkylsulphonyl halogenated pyridines such as 2,3,5,6-tetrachloro-4-(methylsulphonyl)-pyridine and 2,3,6-trichloro-4-(isopropylsulphonyl)-pyridine; tetrachloro-isophthalonitrile; benzimidazomethyl-carbamate; thiocyanatomethylthiobenzthiazole; methylene
 10 bithiocyanate, iodopropargyl-n-butyl-carbamate; triazines such as 2-tert-butylamino-4-ethylamino-6-methylmercapto-1,3,5-triazine and 2-methylthio-4-tert-butylamino-6-cyclopropylamino-1,3,5-triazine; N-(1-methyl-1-naphthyl) maleamide; dichlorofluanide, (fluoro)-captan and (fluoro)-folpet.

Where the composition contains an additional fungicide and/or algicide it
 15 is present preferably at a concentration of less than 50%, more preferably less than 30% and especially less than 10% by weight relative to the amount of ABIT.

As mentioned hereinbefore, fungicides for plastics materials require a careful balance of microbiological activity and volatility and hence any additional fungicide and/or algicide should not significantly impair the properties and performance
 20 in use of the ABIT. For this reason it is preferred that the composition contains only an ABIT.

The 2-alkyl-BIT's of formula 1 are generally liquids at 20 to 25°C and readily dissolve in the plasticiser or stabiliser. The aralkyl-BIT's are solids at 20 to 25°C but can be readily dissolved in the plasticiser or stabiliser if
 25 necessary by heating.

Where higher concentrations of the ABIT are required in the plasticiser or stabiliser and this exceeds its solubility the ABIT may be dispersed in the plasticiser or stabiliser by means of a suitable dispersant particularly a non-ionic dispersant. One preferred dispersant is the reaction product of a hydroxy carboxylic acid and an amine,
 30 or a salt thereof.

Especially preferred are the dispersing agents of formula 2



wherein

Z is a divalent bridging group which is attached to the carbonyl group
 35 through an oxygen or nitrogen atom;

R^3 is a primary, secondary or tertiary amino group or a salt thereof with an acid, or a quaternary ammonium salt; and

Y is a the residue of a polyester chain which together with the -CO- group is derived from a hydroxycarboxylic acid of formula 3




wherein X is a divalent saturated or unsaturated aliphatic group containing at least 8 carbon atoms and in which there are at least 4 carbon atoms between the hydroxy and carboxylic acid groups, or from a mixture of such a hydroxycarboxylic acid and a carboxylic acid which is free from hydroxy groups.

The group X is preferably an alkylene or alkenylene group and preferably contains not greater than 30 carbon atoms, and especially not greater than 20 carbon atoms. Examples of suitable hydroxy carboxylic acids of formula 3 are 12-

hydroxystearic acid, ricinoleic acid, 12-hydroxydecanoic acid and 6-hydroxycaproic acid.


The divalent bridging group represented by Z is preferably of the formula



wherein T^1 is a hydrogen atom, a C_{1-22} -alkyl group or ethylene and A is an alkylene, cycloalkylene, heterocycloalkylene or a hydroxyalkylene group containing from 2 to 6 carbon atoms. When T^1 is alkyl, it is preferably C_{1-6} -alkyl and when A is heterocycloalkylene it is preferably piperazine. Where T^1 and A are both ethylene, the groups T^1 and A together with the nitrogen atom to which they are attached and the nitrogen atom of the amino group R^3 may form a piperazine ring.

As examples of the radicals represented by T^1 there may be mentioned methyl, ethyl, *n*-propyl, *n*-butyl and octadecyl. As examples of the radicals represented by A there may be mentioned ethylene, trimethylene, tetramethylene, hexamethylene and beta-hydroxytrimethylene.

The primary, secondary and tertiary amino groups represented by R^3 are preferably of the formula




5

wherein T^2 and T^3 are each independently hydrogen, C_{1-22} -alkyl, substituted C_{1-22} -alkyl, aralkyl, cycloalkyl, or T^2 and T^3 may together with the nitrogen atom to which they are attached form a 5- or 6-membered ring. When T^2 or T^3 is alkyl, it is preferably C_{1-6} -alkyl, such as methyl. When T^2 or T^3 is cycloalkyl, it is preferably cyclohexyl and when T^2 and T^3 form a ring it is preferably a piperidino, morpholino, or especially a piperazino ring. When T^2 or T^3 is aralkyl it is preferably benzyl.

10

The quaternary ammonium groups represented by R^3 are preferably of the formula :-

15



20

wherein T^4 is hydrogen, C_{1-22} -alkyl, substituted C_{1-22} -alkyl, aralkyl or cycloalkyl and W is an anion. It is preferred that T^4 is C_{1-6} -alkyl, such as methyl.

In the special case where T^2 and T^3 together with the nitrogen atom to which they are attached forms a piperazino ring, either or both nitrogen atoms may be alkylated and either ring nitrogen may form a salt or quaternary ammonium compound.

25

As examples of the radicals represented by T^2 , T^3 and T^4 there may be mentioned alkyl such as methyl, ethyl, n -propyl, n -butyl and octadecyl, hydroxy lower alkyl such as β -hydroxyethyl and cyclohexyl.

30

The acids used to form salts with the amino groups or which contain the anion W can be any inorganic acid or an organic acid, such as hydrochloric acid, sulphuric acid, benzene sulphonic acid methane sulphonic acid or benzoic acid. It is especially preferred that the anion W is that arising from the formation of the quaternary ammonium group, for example chloride, bromide or methosulphate.

The preparation of these dispersing agents is described in our earlier granted patent, GB 1373660.

5 HO - X - COOH 3

10

10

10

15

20

25

30

The amount of dispersant, if present, is preferably from 0.1 to 20%, more preferably from 1 to 10%, especially from 3 to 10% and most especially from 3 to 7% by weight based on the total weight of the composition. The composition also preferably contains a stabiliser to inhibit sedimentation on storage. Examples of stabilisers are naturally occurring clays such as bentonite and particularly organically modified bentonite clay and high MW polymers such as PVC.

As disclosed hereinbefore the ABIT is used as a biocide and especially a fungicide for the protection of plastics materials, especially organic polymeric plastics materials from microbiological degradation. The ABIT is particularly suitable for polyurethane materials and especially organic polymeric materials containing a plasticiser or stabiliser such as those derived from polymerised polyvinylhalides such as polyvinylchloride (PVC). Plasticised PVC is widely used both in the home and industry and is used in clothing, furnishing, shower curtains, flooring, waterproof membranes and the like where the article containing or made from the PVC is exposed to damp or moist conditions.

The amount of plasticiser present in the plastics material varies within wide limits and is determined by the degree of flexibility required in the fabricated material. It is typically between from 1 to 50% by weight of the plastics material.

Thus, as a still further aspect of the invention there is provided a composition comprising an ABIT and a plastics material.

The ABITs are made by processes already known to the art such as those processes disclosed in GB 484,130 wherein a 2-chlorosulphenyl benzoyl chloride is reacted with an alkylamine or an aralkylamine.

Some of the ABITs are novel. Thus, as a further aspect of the invention there is provided a compound of formula 1 wherein R is $-\text{CH}(\text{CH}_3)\text{CH}_2\text{CH}_2\text{CH}_3$, $-\text{CH}(\text{C}_2\text{H}_5)\text{CH}_2\text{CH}_3$, $-\text{CH}_2\text{CH}_2\text{CH}(\text{CH}_3)\text{CH}_3$, $-\text{CH}_2\text{CH}(\text{CH}_3)\text{CH}_3$, $-\text{CH}_2\text{CH}(\text{CH}_3)\text{C}_2\text{H}_5$ and cyclopentyl and R^1 and n are as defined hereinbefore.

The present invention in all aspects is further illustrated and described in the following examples in which all parts are by weight unless indicated to the contrary.

Example 1 and Comparative Example A

An agar recipe was prepared from Potato Dextrose Agar (2 parts; ex Oxoid), Tryptone Soya Broth (10 parts; ex Oxoid) and Agar (14 parts; ex Oxoid) made up to 1 litre and having a pH of 6.5. Aliquots of the ABIT under test were added from a 0.1% w/w solution in dioctylphthalate diluted to 3 ml with dioctylphthalate to give a final

concentration in the agar recipe of 1.25, 2.5, 5, 20 and 30 ppm. After adding the solution of ABIT to the agar and homogenising, plates were cast and allowed to set. These plates were then inoculated with 10^5 spore suspension of the following fungal deteriogens for plastics materials.

5		Aureobasidium pullulans (AP)	CM1	145194
		Fusarium solanii (FS)	CM1	172506
		Penicillium funiculosum (PF)	CM1	114933
		Scopulariopsis brevicaulis (SB)	CM1	49528
10		Streptoverticillium waksmanii (SW)	NCIB	1091

The inoculated plates were incubated for 4 days at 20°C and the concentration of the ABIT determined at which fungal growth was suppressed. The results are given in Table 1 below which refer to the ABIT of formula 1 wherein n is zero and R is as indicated. These show that the 2-ethyl- and 2-(n-propyl)-BIT exhibit overall slightly superior activity compared with the control and better activity against both AP and SB. 2-ethyl-BIT is more active against FS.

Table 1

20	Example or Comp Example	R	<u>AP</u>	<u>FS</u>	<u>PE</u>	<u>SB</u>	<u>SW</u>
	A	Ethyl	20	5	1.25	20	1.25
	1	n-propyl	20	20	1.25	20	1.25
25	Control	-	30	20	1.25	30	1.25

Footnote to Table 1

Control is 2-(n-octyl)-isothiazolin-3-one.

30 Example 2 and Comparative Examples B to D

Example 1 was repeated with the following ABIT's as indicated in Table 2 below and the concentration of chemical determined at which fungal growth was suppressed. The results are given in Table 2 below and show that the 2-(n-butyl)-BIT is more active against the five fungal deteriogens for plastics material than both the 2-(n-hexyl) and 2-(n-octyl)-BIT compounds disclosed in EP 475,123 including higher activity

against SB, especially when compared with 2-(n-octyl)-BIT. In general, the 2-(n-butyl)-BIT is similar to control. Taken with the results of Example 1 there is a general trend of decreasing activity against the plastics material deteriogens as the length of the alkyl chain of the ABIT is increased. The 2-benzyl-BIT exhibits an activity which is intermediate between the (n-hexyl)- and 2-(n-octyl)-BIT's. This decrease in activity with increasing number of carbon atoms in the 2-alkyl chain of the ABIT found for these important fungal deteriogens for plastics material is opposite to that disclosed for fungi such as Aspergillus niger as disclosed in EP 475,123.

Table 2

10

Example or Comp Example	<u>R</u>	<u>AP</u>	<u>FS</u>	<u>PF</u>	<u>SB</u>	<u>SW</u>
2	n-butyl	5	20	1.25	1.25	5
15 B	n-hexyl	5	>30	2.5	2.5	20
C	n-octyl	>30	>30	>30	20	>30
D	benzyl	30	>30	2.5	5	30
Control	-	1.25	20	1.25	2.5	2.5

20

Footnote to Table 2

Control is as stated for Example 1.

Examples 3 and 4 and Comparative Examples E and F

Example 1 was again repeated with the ABIT's listed in Table 3 except that a 50/50 mixture of dioctylphthalate and dioctyladipate was used in place of the dioctylphthalate used in Example 1. The results given in Table 3 below show that n-pentyl-BIT exhibits similar activity to the Control and is superior to n-heptyl-BIT especially against AP and FS. These results are again consistent with decreasing activity as the 2-alkyl chain length of the ABIT is increased. The branched chain compound, 2-ethylbutyl-BIT (Comparative Example E of Table 3) exhibits similar activity to the straight chain analogue (Comparative Example B of Table 2) with some loss of activity against PF. The 2-phenylethyl compound exhibits very high activity against all five deteriogens and is superior in this aspect to the 2-(n-alkyl)-BIT's and also the 2-benzyl-BIT (Comparative Example D of Table 2).

Table 3

Example as			<u>AP</u>	<u>ES</u>	<u>PE</u>	<u>SB</u>	<u>SW</u>
Comp	Example	<u>R</u>					
5							
	3	n-pentyl	5	20	1.25	1.25	1.25
	E	2-ethylbutyl	5	30	20	1.25	20
	F	n-heptyl	20	>30	2.5	1.25	1.25
	4	2-phenylethyl	1.25	1.25	1.25	1.25	1.25
10	Control	-	2.5	20	2.5	1.25	1.25

Footnote to Table 3

Control is as indicated in Table 1.

15 Examples 5 to 7 and Comparative Example A

The ABIT's listed in Table 4 below were heated in air on a Differential Scanning Calorimeter (DSC) from 25-300°C at a 10°C/minute heating rate and the temperature stability determined together with the temperature above which evaporation occurred and also the weight loss by 160°C which represents the temperature at which PVC is fabricated. These results indicate that at least 3 carbon atoms in the alkyl chain of the ABIT is required for adequate thermal stability to withstand the fabrication temperatures for PVC plastics materials. When these results are combined with the antifungal data of Examples 1 to 4 the ABIT wherein R represents C₃₋₅-alkyl is the optimal compromise for a fungicide to protect against fungal deteriogens in plasticised PVC plastics materials. The activity of 2-phenylethyl-BIT combined with its physical properties such as thermal stability show this compound to be superior as an antifungal agent for PVC plastics materials compared with 2-alkyl-BIT's especially when compared with the activity of 2-benzyl-BIT as recorded in Example 2.

Table 4

Example No.	R	Stability temp (°C)	Start of evaporation (°C)	Weight loss (%) by 160°C
5	n-propyl	240	130	5.5
6	n-butyl	260	96 *	5.1
7	2-phenylethyl	>250	>200	0
A	ethyl	235	107	10.6

Footnote to Table 4

* low figure is thought due to a trace of solvent

Examples 8 to 15 and Comparative Examples A, G and H

The fungal esterase activity in PVC was determined by the following fluorescein diacetate protocol.

PVC coupons were prepared by adding the ABIT from the requisite aliquot of a 1% (w/w) solution of the compound dissolved in 50/50 dioctylphthalate and dioctyladipate to give 100, 250, 750, 2250 and 6750 ppm chemical in the final PVC coupon.

The PVC coupon had the following composition :-

100 parts, PVC resin (Corvic S 67/100)
 2 parts, Zn/Ca stabiliser (Lankromark LN 138)
 3 parts, Co plasticiser (Lankroflex ED6)
 25 parts, plasticiser (di-iso-octylphthalate) (DOP)
 25 parts, plasticiser (di-octyladipate) (DOA)
 0.5 parts, calcium stearate dispersant
 0.2 parts, stearic acid mould-release agent
 ppm ABIT

A PVC sheet was prepared by mixing the above ingredients until homogeneous and then rolling and mixing on a two-roll mill for 90 seconds at 160°C.

The sheet was then cut into pieces and coupons (2cm x 5cm) were prepared by pressing between steel sheets at 160°C and 8 tons pressure for 5 minutes.

Duplicate PVC coupons were placed on the surface of moistened vermiculate beds and sprayed with a 10^5 fungal spore suspension of the five fungal
5 deteriogens listed in Example 1 which had been prepared in a minimum salts solution comprising 2.0 parts sodium nitrate, 0.7 part potassium dihydrogen phosphate, 0.3 part dipotassium hydrogen phosphate, 0.5 part potassium chloride, 0.5 part, magnesium sulphate heptahydrate and 0.01 part ferrous sulphate heptahydrate all in 1 litre giving a pH value of 6 to 6.5.

10 The inoculated coupons were then incubated for 7 days at 21°C. The coupons were then removed and placed in individual bottles containing 6 ml buffer solution at pH 7.6 prepared from 0.06M disodium hydrogen phosphate (862.5ml) and 0.06M sodium dihydrogen orthophosphate (137.5 ml) and also 1ml fluorescein diacetate (FDA) in dry acetone. The samples were then incubated for 30 minutes at 37°C in order
15 to develop the colour reaction. The absorbance of each solution was measured at 490 nm using a spectrophotometer. This colour reaction is a measure of esterase expressed by the fungi and indicates fungal deterioration of the plasticiser.

Prior to evaluation by FDA analysis, the coupons were also assessed visually for fungal growth using a stereo-microscope after 1 months incubation at 25°C
20 and 95% relative humidity.

Parallel experiments were also carried out on coupons which had been weathered for 100 hours in an Atlas ES-25 Weatherometer at cam setting 7 with a 2 minute water cycle every 10 minutes and continuous UV radiation.

The results are given in Tables 5 and 6 below.

25 The FDA analysis of Table 5 for the unweathered samples at the 100 and 250 ppm level confirms the reduction in activity against the five fungal deteriogens for plastics materials with increasing number of carbon atoms in the 2-alkyl chain. This is manifest even though some loss of ABIT must have occurred in the case of the lower alkyl chain analogues during fabrication of the coupons. After weathering, however, the
30 trend is reversed and protection against the fungi increased with the increasing number of carbon atoms in the 2-alkyl group. This is most clearly seen at the 750 ppm level of ABIT.

The trend in the fungal growth data of Table 6 is less clear although there is again a trend to reduced activity with increasing number of carbon atoms in the 2-alkyl
35 group. This is most clearly shown by the unweathered data at 250 and 750 ppm applied

ABIT. The trends after weathering are less clear. However, when the data of Tables 1 to 6 are combined, ABIT's suitable for plastics materials are a compromise between high temperature stability, volatility and activity against fungal deteriogens. In the case of ABIT's containing a 2-alkyl chain, this compromise is centred on the 2-(C₃₋₅-alkyl)-BIT's.

5

TABLE 5
FDA ANALYSIS

Example and			Test chemical concentration (ppm)					
Comp	example	R	weathering	100	250	750	2250	6750
10	8	n-propyl	u	sl	tr	-	-	ND
			w	++	++	sl	-	ND
	9	n-butyl	u	sl	sl	-	-	ND
			w	+	++	tr	-	ND
15	10	n-pentyl-	u	tr	-	-	-	ND
			w	tr	sl	-	-	ND
	11	2-phenyl-ethyl	u	-	-	-	-	ND
			w	tr	-	-	-	
20	A	ethyl	u	tr	-	-	-	ND
			w	++	sl	++	-	ND
	G		u	ND	sl	sl	-	-
			w	ND	+	sl	-	-
	H		u	+				
			w	++				
25	Control		u	++				
			w	++				

Footnote to Table 5

30

u is unweathered	- is no absorbance at 490 nm	
w is weathered	tr is less than 0.1 absorbance at 490 nm	
ND is not determined	sl is 0.1-0.25 absorbance at 490nm	
G is trichloromethylmercaptophthalimide	+	is 0.25-0.5 absorbance at 490nm
H is oxy-bis-10,10-phenoxarsine	++	is greater than 0.5 absorbance at 490nm

35

TABLE 6
FUNGAL GROWTH

5	Example and Comp R		Test chemical concentration (ppm)						
			weathering	100	250	300	750	2250	6750
10	12	n-propyl	u	3,3	0,0	ND	0,0	0,0	ND
			w	5,5	5,5	ND	3,3	0,0	ND
	13	n-butyl	u	1,1	1,1	ND	0,0	0,0	ND
			w	5,5	4,5	ND	4,5	0,0	ND
	14	n-pentyl	u	4,4	3,2	ND	2,3	2,1	ND
			w	4,3	4,4	ND	3,2	3,3	ND
	15	2-phenyl-ethyl	u	4,2	0,0	ND	0,0	0,0	ND
			w	5,5	5,5	ND	3,3	0,0	ND
	A	ethyl	u	1,1	0,0	ND	0,0	0,0	ND
			w	5,5	3,2	ND	4,2	0,0	ND
20	G		u	ND	2,2	ND	1,1	1,1	0,0
			w	ND	4,3	ND	2,2	1,1	0,0
	H		u	4,4	ND	0,0	ND	ND	ND
			w	5,5	ND	5,5	ND	ND	ND
	Control		u	5,5	ND				
			w	5,5	ND				

25 Footnote to Table 6

The legends n,w, and ND have the same meaning as in Table 5

G is trichloromethylmercaptophthalimide

H is oxy-bis-10,10-phenoxarsine

30 0 is no growth on test pieces

1 is less than 1% surface growth

2 is 1-10% surface growth

3 is 10-30% surface growth

4 is 30-70% surface growth

35 5 is greater than 70% surface growth

Example 16a) Preparation of 2,2'-dithiodi-N-(3-methylbutyl)-dibenzamide

Dithiodibenzoyl chloride (6.86 parts, 0.02M) was added in portions with stirring at 0 to 5°C to a solution of isoamylamine (3.47 parts, 0.04M ex Aldrich) and triethylamine (4.04 parts, 0.04M ex Aldrich) in diethylether. An immediate precipitate formed. The reaction mix was stirred for 16 hours whilst allowing the temperature to rise to about 20°C. The ether was then evaporated and the product washed with methanol (50ml) and water (50ml). The product was finally recrystallised from methanol as a white solid (6 parts, 69% theory, mp =181-183°C.

Elemental analysis :

Theory :- 64.8%C, 7.3%H, 6.3%N, 14.4%S

Found :- 64.1%C, 6.9%H, 6.3%N, 14.4%S

b) Preparation of 2-(3-methylbutyl)-benzisothiazolin-3-one

The bisamide (5.7 part, 0.0128M) prepared as described above was dissolved in pyridine (75ml) and iodine (3.26 parts, 0.0128M) was added portionwise with stirring at 20 to 25°C. Initially, the iodine was rapidly decolourised but towards the end of the addition of iodine the reaction mix became yellow-brown. After stirring for a further 2 hours at 20 to 25°C the reaction mix became almost colourless. The pyridine was then evaporated and the product dissolved in toluene which was washed with aqueous sodium thiosulphate followed with water to remove traces of iodine. The toluene was then evaporated giving a pale yellow oil (5.3 parts, 94% theory) which solidified on standing. The product was recrystallised from hexane mp = 55-56°C.

Elemental analysis

Theory :- 65.1%C, 6.6%H, 6.4%N, 14.6%S

Found :- 65.1%C, 6.8%H, 6.3%N, 14.5%S

Example 17Preparation of 2-(1-methylbutyl)benzisothiazolin-3-one

2-Chlorosulphenylbenzoyl chloride (6 parts, 0.029M) dissolved in diethylether (30ml) was added dropwise at 0 to 3°C to a stirred solution of 1-methylbutylamine (7.36 parts, 0.84M ex Aldrich) in diethylether (30ml). The reactants were stirred for 16 hours whilst allowing the temperature to rise to about 20°C. The ether solution was then screened, washed with water and dried over magnesium sulphate. After evaporation of the ether, the product was obtained as a pale yellow gum

(5.5 parts, 86% theory) which gradually solidified on standing. This was recrystallised from hexane. mp = 52-54°C.

Elemental analysis

Theory :- 65.3%C, 7.2%H, 6.5%N, 14.4%S

5 Found :- 65.1%C, 6.8%H, 6.3%N, 14.5%S

Example 18

Preparation of 2-(1-ethylpropyl)benzothiazolin-3-one

10 This was prepared in analogous manner to that described in Example 17 except using 2-chlorosulphonyl chloride (6.21 parts, 0.03M) and 1-ethylbutylamine (8.7 parts, 0.2M ex Aldrich). The product was obtained as a pale yellow gum (6.4 parts, 96% theory) which solidified on standing. It was recrystallised from hexane mp = 80-82°C.

Elemental analysis

Theory :- 64.8%C, 5.7%H, 6.3%N, 14.5%S

15 Found :- 65.1%C, 6.8%H, 6.3%N, 14.5%S

Example 19

Preparation of 2-cyclopentylisothiazolin-3-one

20 This was prepared in analogous manner to that described in Example 17 except using 2-chlorosulphenylbenzoyl chloride (5.175 parts, 0.025M) and cyclopentylamine (8.52 parts, 0.1M ex Aldrich). The product was obtained as a yellow oil (5.9 parts) which was recrystallised form hexane mp 87-88°C.


Example 20

25 Preparation of 2-(2-methylpropyl) benzisothiazolin-3-one

This was prepared by the process described in Example 17 except using 2-chlorosulphenylbenzoyl chloride (4.14 parts, 0.02M) and isobutylamine (7.95 parts, 0.08M). The product (4 parts, 97% theory) was obtained as a pale yellow oil.

30 Examples 21 to 25

The following bisamides of formula A were prepare by the process described in Example 19(a) and converted to the substituted benzoisothiazolin-3-one (BIT) of formula B by the process described in Example 19(b).



The analytic data and melting points are given in Tables 7a and 7b below wherein the position of substituent R¹ is given for the BIT.

10 The 2-alkyl BIT's and 2-aralkyl-BIT's, the preparation of which is described in Examples 21 to 25, exhibit similar protection to 2-n-butyl-BIT against deterogens for plastics materials.

Table 7a


Example	R	R'	BISAMIDE ELEMENTAL ANALYSIS (%)									
			THEORY				FOUND				mp (°C)	
			C	H	N	S	C	H	N	S		
21	-CH ₂ CH(CH ₃)C ₂ H ₅	H	64.9	7.2	6.3	14.4	65.1	7.3	6.3	12.8	174-5	
22	-(CH ₂) ₂ CH ₃	6Cl-										
23	-(CH ₂) ₂ Ph	6Cl-	62.0	4.5	4.8	11.0	62.0	4.5	4.9	11.0	240-2	
24	-(CH ₂) ₃ CH ₃	6Cl-										
25	-(CH ₂) ₃ CH ₃	5Cl-	55.2	5.4	5.8	13.2	55.1	5.4	5.8	13.9	230-2	

Table 7b

Example	R	R'	BIT ELEMENTAL ANALYSIS (%)									
			THEORY					FOUND				
			C	H	N	S	C	H	N	S	mp (°C)	
21	-CH ₂ CH(CH ₃)C ₂ H ₅	H	65.2	6.8	6.3	14.5	64.6	6.8	6.0	14.1	OIL	
22	-(CH ₂) ₂ CH ₃	6Cl-	52.8	4.4	6.2	14.1	53.2	4.5	6.6	13.6		
23	-(CH ₂) ₂ Ph	6Cl-	62.2	4.1	4.8	11.0	62.7	4.1	5.0	11.3	143-5	
24	-(CH ₂) ₃ CH ₃	6Cl-	54.7	5.0	5.8	13.3	55.5	5.1	6.0	13.5	105-6	
25	-(CH ₂) ₃ CH ₃	5Cl-	54.7	5.0	5.8	13.3	56.1	5.1	6.0	14.2	75-6	

CLAIMS

1. The use of a 2-alkyl or 2-aralkyl-BIT derivative of formula 1 as a fungicide for plastics materials.



wherein


- 10 R^1 is hydroxy, halogen, C_{1-4} -alkyl or C_{1-4} -alkoxy;
 R is C_{3-5} -alkyl, cycloalkyl or aralkyl which contains at least 2 carbon atoms linking the aryl group to the nitrogen atom and where the alkyl or aryl group may be optionally substituted; and
 n is from 0 to 4.

- 15 2. The use as claimed in claim 1 wherein n is zero.

3. The use as claimed in either claim 1 or claim 2 wherein R contains 4 carbon atoms.

- 20 4. The use as claimed in either 1 or claim 2 wherein the BIT derivative is 2-(n-butyl)-BIT or 2-phenylethyl-BIT.

- 25 5. A composition comprising a plasticiser or stabiliser and a 2-alkyl or 2-aralkyl-BIT derivative of formula 1



wherein

- 35 R^1 is hydroxy, halogen, C_{1-4} -alkyl or C_{1-4} -alkoxy;
 R is C_{3-5} -alkyl, cycloalkyl or aralkyl which contains at least 2 carbon atoms linking the aryl group to the nitrogen atom and where the alkyl or aryl group may be optionally substituted; and

n is from 0 to 4.

6. A composition as claimed in claim 5 wherein the plasticiser or stabiliser is an ester or epoxidised vegetable oil.

5

7. A composition as claimed in claim 6 wherein the ester is di-octylphthalate, dioctyladipate or mixture thereof.

10


8. A composition as claimed in claim 6 wherein the vegetable oil is soya bean oil.

9. A composition as claimed in any one of claims 5 to 8 which further comprises a dispersant.

15

10. A composition which comprises a plastics material and a 2-alkyl or 2-aralkyl-BIT of formula 1

20



wherein

R¹ is hydroxy, halogen, C₁₋₄-alkyl or C₁₋₄-alkoxy;

25


R is C₃₋₅-alkyl, cycloalkyl or aralkyl which contains at least 2 carbon atoms linking the aryl group to the nitrogen atom and where the alkyl or aryl group may be optionally substituted; and

n is from 0 to 4.

30

11. A composition as claimed in claim 10 wherein the plastics material is polyurethane or plasticised PVC.

12. A compound of formula 1



wherein

10 R is -CH(CH₃)CH₂CH₂CH₃, -CH(C₂H₅)CH₂CH₃, -CH₂CH₂CH(CH₃)CH₃,
-CH₂CH(CH₃)CH₃, -CH₂CH(CH₃)C₂H₅ or cyclopentyl; and R¹ and n are as defined in
claim 1.

INTERNATIONAL SEARCH REPORT

Int. Application No

PCT/GB 95/02951

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 A01N43/80 C08K5/47 C07D275/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08K C07D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB,A,848 130 (ICI) 14 September 1960 cited in the application see claims 1,16	1-12
X	--- US,A,3 517 022 (G.A. MILLER ET AL.) 23 June 1970 cited in the application see column 1, line 51 - column 2, line 14 see column 7, line 47 - line 55 see column 8, line 1 - line 6	1-12
X	--- US,A,3 862 955 (J.C. GRIVAS) 28 January 1975 see column 3, line 3 - line 36 see column 8, line 49 - line 60 --- -/--	1-12

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

21 March 1996

Date of mailing of the international search report

03.04.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Decorte, D

INTERNATIONAL SEARCH REPORT

Inter mal Application No
PCT/GB 95/02951

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	CHEMICAL ABSTRACTS, vol. 68, no. 25, 17 June 1968 Columbus, Ohio, US; abstract no. 114493, R. PONCI ET AL. 'Bis(2-carboxyphenyl) disulfide diamides and benzisothiazolones. Influence of butyl groups on antifungal activity.' see page 11036, column 1, line 1 - line 4 & FARMACO ED. SCI., vol. 22, no. 12, 1967 pages 999-1010, ---	1,3-12
X	US,A,2 870 015 (C.F.H. ALLEN ET AL.) 20 January 1959 see column 1, line 60 - column 2, line 9 ---	12
A	WO,A,94 20479 (ZENECA) 15 September 1994 see claims 1,7,11 see page 7, line 13 - line 20 see page 15; table 2 ---	1-11
A	EP,A,0 475 123 (RIEDEL-DE HAEN) 18 March 1992 cited in the application see claims ---	1-11
A	GB,A,1 531 431 (ICI) 8 November 1978 cited in the application see claims -----	1-11

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 95/02951

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB-A-848130		NONE	
US-A-3517022	23-06-70	NONE	
US-A-3862955	28-01-75	BE-A- 766264	26-10-71
		CH-A- 560708	15-04-75
		DE-A- 2119730	11-11-71
		FR-A, B 2104745	21-04-72
		GB-A- 1306493	14-02-73
		NL-A- 7105597	29-10-71
		SE-B- 392103	14-03-77
US-A-2870015	20-01-59	BE-A- 565380	
		FR-A- 1202249	08-01-60
		GB-A- 884514	
WO-A-9420479	15-09-94	AU-B- 6009394	26-09-94
		CA-A- 2155305	15-09-94
		EP-A- 0688321	27-12-95
		FI-A- 954211	08-09-95
		NO-A- 953547	08-09-95
		ZA-A- 9401069	10-09-94
EP-A-475123	18-03-92	DE-A- 4027378	05-03-92
		AT-T- 116522	15-01-95
		DE-D- 59104132	16-02-95
		ES-T- 2069142	01-05-95
GB-A-1531431	08-11-78	AU-B- 1031476	21-07-77